

POWERED BY **Dialog**

Nontoxic polyolefin moulding compositions - contain aluminium silicate, silica and polyester plasticisers

Patent Assignee: SUMITOMO BAKELITE CO

Patent Family

Patent Number	Kind	Date	Application Number	Kind	Date	Week	Type
JP 50123148	A	19750927				197742	B

Priority Applications (Number Kind Date): JP 7429921 A (19740318)

Abstract:

JP 50123148 A

Compsns. of polyethylene (I) or polypropylene 100, Al silicate(II) 10-150 silica (III) 10-50, and polyester plasticisers 0.5-40 pts. are nontoxic and have good mouldability and antistatic properties.

In an example a compsn. of high-d I 100, II 40, III 30, and polyester plasticiser 5 pts. had half life of charged electricity 3 sec. no toxicity and good mouldability compared with a similar compsn. contg. II 15, III 0, and plasticiser 20 pts.

Derwent World Patents Index

© 2005 Derwent Information Ltd. All rights reserved.

Dialog® File Number 351 Accession Number 1853626